

**TECHNICAL DATA SHEET****STONE@Guard**

~ Acrylic Interior &amp; Exterior Stone Dressing ~

**Document No: TB-OP-01**

**SANCoro®** STONE@Guard is formulated with acrylic resin. It gives high gloss retention, excellent brushability and abrasion resistance. It is also excellent in acid and alkali resistance and provides a coat of high sheen smooth finish. Suitable for structures with dull and matt cobblestone or tiles surfaces.

<b>Usage</b>	Recommended used for cobblestone pave way or car porch. It is also suitable on matt tiles surface structures.	
<b>Pack Size</b>	1 litre, 5 litres and 18 litres.	
<b>Composition</b>	Binder	: Acrylic Resin
	Vehicle	: Aromatic Hydrocarbon
<b>Technical Data</b>	Texture	: High Sheen Smooth Finish
	Colour	: Clear
	Theoretical Coverage	: Approx. 15 - 17m <sup>2</sup> /litre (Depending on surface evenness)
	Drying Time	Single coat at standard thickness (28°C, 50% RH)
		: Touch Dry ≤ 3 hours
		: Hard Dry ≤ 8 hours
	Recoating Time	: 6 hours
	Thinner/Cleaner	: Mineral Spirit
<b>Application</b>	Brush/Roller	: Ready for use
	Conventional Air Spray	: Ready for use
	Airless Spray	: Ready for use
<b>Surface Preparation</b>	Cobblestone or Tiles	: Surfaces must be sound, clean, dry and free from all defective or poorly adhering materials, dirt, sands, grease or wax.
<b>Shelf Life</b>	2 years at ambient temperature in unopened containers.	

**Paint Guide**

Surface Condition	Finishing - To Paint 2 Coats
New Cobblestone/Tiles	<b>SANCoro®</b> STONE@Guard
Previously Painted Cobblestone/Tiles	<b>SANCoro®</b> STONE@Guard

**Safety, Health and Environmental Information**

When applying paint, it is advisable to wear eye protection and suitable gloves.

In case of contact with eye, rinse with plenty of water immediately and seek medical advice.

Remove splashes of paint from skin by using soap or water.

Keep container tightly closed and away from food, drinks, animal feed and out of the reach of children.

Ensure good ventilation during application and drying.

Paint must always be stored in upright position and a cool place.

Dispose off any paint waste in accordance with the appropriate Environmental Quality Regulations.

Refer to Safety Data Sheet for complete product safety information.

The above information is given to the best of our knowledge based on our existing laboratory test and practical experience, however since conditions of actual use are beyond our control any recommendations and suggestions are made without warranty, express or implied and we reserve the right to alter the given data without prior notice.

**SANCORA PAINTS INDUSTRIES SDN BHD** (19733-T)

(Wholly Owned Subsidiary Of Kansai Paint Asia Pacific Sdn Bhd)

Lot 8206, Kawasan Perusahaan Kamunting, 34600 Kamunting, Perak, Malaysia

Tel: +605-891 8777 (8 Lines) Fax: +605-891 2277 Email: info@sancora.com

Website: [www.sancora.com](http://www.sancora.com) Facebook: [www.facebook.com/sancorapaint](http://www.facebook.com/sancorapaint)

## RISALAH DATA TEKNIKAL

### STONE@Guard

~ Acrylic Interior & Exterior Stone Dressing ~

No Dokumen: TB-OP-01

SANCor<sup>®</sup> STONE@Guard adalah diformulasi dengan resin akrilik. Ia memberikan pengekalan kilau yang tinggi, kebolehan memberus dan daya tahan calar yang baik. Ia juga sangat bagus terhadap daya tahan asid dan alkali dan memberikan satu lapisan dengan kemasan licin kilauan tinggi. Sesuai untuk struktur-struktur dengan permukaan jubin atau batu-batu hiasan yang kusam dan matt.

<b>Penggunaan</b>	Disyorkan untuk laluan batu-batu hiasan atau anjung kereta. Juga sesuai untuk struktur permukaan jubin yang kusam.	
<b>Saiz Pembungkusan</b>	1 liter, 5 liter dan 18 liter.	
<b>Komposisi</b>	Binder	: Resin Akrilik
	Pelarut	: Hidrokarbon Aromatik
		:
<b>Data Teknikal</b>	Tekstur	: Kemasan Licin Kilauan Tinggi
	Warna	: Jernih
	Liputan Teori	: Anggaran 15 - 17m <sup>2</sup> /liter (Bergantung pada kelicinan permukaan)
	Tempoh Kering	Satu lapisan dengan ketebalan standard (28°C, 50% RH)
		: Kering Disentuh ≤ 3 jam
		: Kering Sempurna ≤ 8 jam
	Tempoh Lapisan Semula	: 6 jam
	Pencair/Pencuci	: Spirit Mineral
<b>Aplikasi</b>	Berus/Penggelek	: Sedia untuk digunakan.
	Penyembur Udara Konvensional	: Sedia untuk digunakan.
	Penyembur Tanpa Udara	: Sedia untuk digunakan.
<b>Penyediaan Permukaan</b>	Batu-batu Hiasan atau Jubin	: Permukaan mesti licin, bersih, kering dan bebas daripada sebarang kekotoran, minyak atau wax.
<b>Jangka Hayat</b>	2 tahun pada suhu ambien dalam bekas tertutup.	

#### Panduan Mengecat

Keadaan Permukaan	Kemasan – Cat 2 Lapisan
Batu-batu Hiasan/Jubin Baru	SANCor <sup>®</sup> STONE@Guard
Batu-batu Hiasan/Jubin yang Pernah Dicat	SANCor <sup>®</sup> STONE@Guard

#### Infomasi Keselamatan, Kesihatan dan Persekitaran

Semasa mengecat adalah disyorkan memakai perlindungan mata dan sarung tangan yang sesuai.  
 Jika mata terkena cat, cuci dengan air yang banyak dan segera berjumpa doktor.  
 Bersihkan sebarang cat yang terkena pada kulit dengan sabun dan air.  
 Pastikan tong cat ditutup rapat dan jauhkan daripada makanan, minuman dan kanak-kanak.  
 Pastikan ada ventilasi yang baik semasa pengecatan dan pengeringan.  
 Tong cat mesti disimpan dalam keadaan tegak dan kawasan yang sejuk.  
 Buangkan semua sisa cat menurut Peraturan Kualiti Alam Sekitar.  
 Rujuk kepada lembaran SDS untuk maklumat yang lebih terperinci.

Informasi yang diberikan diatas adalah berdasarkan pengetahuan kami yang diperoleh dari ujian makmal dan pengalaman praktikal, walaubagaimanapun, penggunaan pada keadaan semasa adalah diluar kawalan kami dan sebarang cadangan adalah dibuat tanpa jaminan, nyata atau tersirat dan kami berhak mengubah data yang diberi tanpa pemberitahuan notis dahulu.

**SANCORA PAINTS INDUSTRIES SDN BHD** (19733-T)

(Wholly Owned Subsidiary Of Kansai Paint Asia Pacific Sdn Bhd)

Lot 8206, Kawasan Perusahaan Kamunting, 34600 Kamunting, Perak, Malaysia

Tel: +605-891 8777 (8 Lines) Fax: +605-891 2277 Email: info@sancora.com

Website: [www.sancora.com](http://www.sancora.com) Facebook: [www.facebook.com/sancorapaint](https://www.facebook.com/sancorapaint)